AMENDMENT OF SOLICITATI	ON/MODIFICATI	ON OF CONTRACT	1. Contract		Page 1 Of 6
2. Amendment/Modification No.	3. Effective Date	4. Requisition/Purchase Req			o. (If applicable)
0001	2007MAR21	SEE SCHEDULE			
6. Issued By	Code W56HZV	7. Administered By (If other	than Item 6)		Code
U.S. ARMY TACOM LCMC  AMSTA-AQ-AHPC  TERRY ZIELINSKI (586)574-5833  WARREN, MICHIGAN 48397-5000  HTTP://CONTRACTING.TACOM.ARMY.MIL EMAIL: ZIELINST@TACOM.ARMY.MIL		SCD	PAS	AD	РРТ
8. Name And Address Of Contractor (No., Stre	et. City. County. State and		9A. Amendme		
of value and address of contractor (140, 51)	cei, city, county, state and	1 Zip Code)			1011 1101
			W56HZV-07-Q-		
			2007MAR07	: Item 11)	
			10A. Modifica	tion Of Contra	act/Order No.
			10B. Dated (Se	ee Item 13)	
Code Facility Code	NAME AND A COLUMN AS A DOMESTIC		OT LOTE LETON	TG.	
		ES TO AMENDMENTS OF S			
I lie above numbered solicitation is amend	2007APR24 01:00pm	The hour and date specified f	or receipt of Of	fers	
Offers must acknowledge receipt of this ame (a) By completing items 8 and 15, and return offer submitted; or (c) By separate letter or ACKNOWLEDGMENT TO BE RECEIVED SPECIFIED MAY RESULT IN REJECTION change may be made by telegram or letter, popening hour and date specified.  12. Accounting And Appropriation Data (If received)	ning <u>2</u> signed copies of telegram which includes a D AT THE PLACE DESIGN OF YOUR OFFER. If provided each telegram or	of the amendments: (b) By ack reference to the solicitation an GNATED FOR THE RECEIPT by virtue of this amendment yo	nowledging reco nd amendment r TOF OFFERS I ou desire to char	eipt of this am numbers. FAI PRIOR TO TI nge an offer al	e ndment on each copy of the LURE OF YOUR HE HOUR AND DATE ready submitted, such
13. THIS		O MODIFICATIONS OF CO act/Order No. As Described In		DERS	
A. This Change Order is Issued Pursua The Contract/Order No. In Item 10.	nt To:			hanges Set For	th In Item 14 Are Made In
B. The Above Numbered Contract/Orde Set Forth In Item 14, Pursuant To T		θ ,	uch as changes	in paying offic	e, appropriation data, etc.)
C. This Supplemental Agreement Is Ent	tered Into Pursuant To Au	thority Of:			
D. Other (Specify type of modification a	and authority)				
E. IMPORTANT: Contractor is not,  14. Description Of Amendment/Modification (	<u> </u>	this document and return		copies to the Is	
•	organized by OCI section	neutings, meruting solicitation	m contract subje	cet matter whe	ic icusioic.
SEE SECOND PAGE FOR DESCRIPTION					
Except as provided herein, all terms and condi and effect.	tions of the document refe	renced in item 9A or 10A, as h	eretofore chang	ged, remains u	nchanged and in full force
15A. Name And Title Of Signer (Type or print)	)	16A. Name And Title	Of Contracting	Officer (Type	or print)
15B. Contractor/Offeror	15C. Date Signed	16B. United States Of	America		16C. Date Signed
		By	/SIGNED/		
(Signature of person authorized to sign)	_	(Signature o	of Contracting (		
NSN 7540-01-152-8070		30-105-02		STANDARD	FORM 30 (REV. 10-83)

CONTINUATION SHEET	Reference No. of Document Be	Page 2 of 6	
CONTINUATION SHEET	PHN/SHN W56HZV-07-Q-0449	MOD/AMD 0001	

### Name of Offeror or Contractor:

#### SUPPLEMENTAL INFORMATION

- 1. The purpose of Amendment 0001 is to inform all offerors that this solicitation is competitive w/purchase parts estimated at 10-50% of the total item cost. The purchase parts are 12293287-4,2589945-5 and 12295791-10.
- 2. In addition, special process clauses along with purchase parts clauses are added to this amendment.
- 3. The closing date is hereby changed from April 10,2006 to April 24,2006 at 1300.
- 4. All other terms and conditions remain unchanged.

\*\*\* END OF NARRATIVE A 0002 \*\*\*

## **CONTINUATION SHEET**

#### Reference No. of Document Being Continued

PIIN/SIIN W56HZV-07-Q-0449

MOD/AMD 0001

**Page** 3 of 6

#### Name of Offeror or Contractor:

DESCRIPTION/SPECIFICATIONS/WORK STATEMENT

Status	Regulatory Cite	Title	Date
1 ADDED	52.211-4011	ACQUISITION OF MANUFACTURER'S PART NUMBER: COMPONENTS	FEB/1998
	(TACOM)		

One or more of the drawings for part of the contract item set forth in the Schedule and in the Technical Data Package specify manufacturer's part numbers. Since complete Government technical data for such part or parts are not available, it is understood that the Contractor, by accepting this contract, agrees to furnish only the listed manufacturer's part number(s) for those components of the contract item, except as provided in the provision entitled NOTICE REGARDING "SOURCE-CONTROLLED" COMPONENTS. (In Section L or near the end of this solicitation.) It is further understood and agreed that references to manufacturer's part numbers herein shall be deemed to include all changes or revisions thereto which the approved manufacturer has made effective as of the first date of delivery of any of the items under this contract; provided, that no change or revision that affects the interchangeability (ability to be interchanged with previous parts and to match with all mating parts when assembled) of the listed manufacturer's part shall be incorporated into the contract item without the prior written approval of the Procuring Contracting Officer.

[End of Clause]

INSPECTION AND ACCEPTANCE

2 ADDED 52.211-4016 CARC PAINT-PRETREATMENT REQUIREMENTS FOR FERROUS, GALVANIZED AND DEC/2005 (TACOM) ALUMINUM SURFACES

(a) Ferrous and galvanized surfaces shall be cleaned and pretreated with a Type 1, zinc phosphate system per TT-C-490. Alternate pretreatment systems for ferrous substances must meet the performance tests specified in paragraphs 3.5.7, 3.5.8, 4.2.7, and 4.2.8 of TT-C-490.

Corrosion resistance tests on steel substrates will be conducted on a monthly basis using two test coupons. This test frequency shall begin once the process has been found to be in statistical control.

Unless otherwise specified, MIL-P-53022 and -53030 primers on steel substrates shall be salt spray tested for 336 hours (ASTM B117). All electrocoat primers on steel substrates shall be tested for 1000 hours. Test coupons shall be scraped at a 30 degree contact angle (approximate), with a one inch (approximate) metal blade such as a putty knife, between 24 and 168 hours after removal from the neutral salt spray cabinet for coupon evaluation. All TT-C-490E (Type I) zinc phosphate pretreatment systems must be documented and approved by the procuring activity prior to use. The procedure containing all the elements specified in paragraph 3.2 of TT-C-490 shall be available for review at the applicator's facility.

The prime contractor shall notify the procuring activity no less than 45 days prior to start of pretreatment and painting that the procedure is available for review and approval. Qualification will consist of verification that the process with its controls can meet the performance requirements in the specification.

Re-qualification of the process shall be required if the process is changed outside the limits defined in the TACOM letter of system approval provided to the application facility.

Note: Zinc phosphate systems for galvanized surfaces require different controls than those for steel. Hot dipped galvanized surfaces are highly prone to chloride contamination from the galvanizing flux process. This contaminant must be removed prior to pretreatment for the coating system to pass these performance tests. The test coupons must duplicate the production painting process as closely as possible. If production is force cured, test coupons shall be cured in an identical manner.

- (b) Qualification and control of pretreatment systems for galvanized substrates shall be performed using Accelerated Corrosion Test protocol contained in GM 9540P rather than salt spray. Test coupons with pretreatment and primer only shall be cured for seven days, and then scribed through the primer to the substrate. After 40 cycles of test exposure, the test coupons shall be scraped at a 30 degree contact angle (approximate), with a one inch (approximate) metal blade such as a putty knife, both parallel and perpendicular to the scribe after removal from the test chamber for coupon evaluation. There shall be no more than 3 mm of corrosion, blistering, or loss of paint adhesion from the scribe line and no more than 5 blisters in the field with none greater than 1 mm diameter. This test shall be performed at three month intervals (two test coupons) to ensure that the process remains in control.
- (c) Aluminum substrates require a chromate conversion coating per MIL-C-5541E (or alternate, see note below). If any other alternate pretreatment is considered, it must pass 120 cycles of GM9540P with a design of experiments test matrix approved by the procuring activity. After completion of the cyclic salt environment exposure, the panels shall be scraped as described above, and shall have no more than 0.5 mm paint loss (creep-back) from the scribe. In addition, there shall be no more than 5 blisters in the field with none larger than 1mm diameter. After completion of the 120 cycle corrosion resistance test evaluation, each test panel will be subjected

## **CONTINUATION SHEET**

#### Reference No. of Document Being Continued

PIIN/SIIN W56HZV-07-Q-0449

MOD/AMD 0001

Page 4 of 6

#### Name of Offeror or Contractor:

to cross hatch tape test (ASTM D3359, method b 6 cut pattern. minimum tape adhesion rating of 45 oz. per inch of width) and shall be done no closer than 12 mm from any panel edge or the scribe. The removal of two or more complete squares of primer shall constitute failure. Any alternate system must demonstrate its ability to pass both corrosion and adhesion tests on 5 consecutive days of production to be considered acceptable.

For information purposes:

Note: The only alternative products which have demonstrated their ability to meet these requirements for 5000 and 6000 series aluminum alloys are Alodine 5200 and Alodine 5700. Documented process controls shall be established which comply with the manufacturer's technical bulletin. Spray-to-waste systems will require fewer process controls than an immersion process.

- (d) The use of TT-C-490E Type III: Vinyl Wash Primer (DOD-P-15328) has hexavalent chromium content and high VOC level. Bonderite 7400 is an approved, environmentally friendly alternative for wash primer. The application and control process shall be documented. This product is subject to the same salt spray requirements as a zinc phosphated product. The number of process controls for this product is dependent upon its method of application. The specific controls shall be in agreement with the product manufacturer's technical bulletin to provide the level of performance required for zinc phosphated substrates. Spray-to-waste applications will require fewer process controls than an immersion process.
- (e) Acceptance of production painted parts is contingent upon the painted surface meeting the dry film thickness and cross hatch adhesion requirements. The CARC painted surface shall be free of any blisters, pores or coverage voids.

3 ADDED 52.211-4030

BASIC APPLICATION AND TESTING REQUIREMENTS FOR CHEMICAL AGENT RESISTANT COATINGS (CARC) ON METALLIC SURFACES

DEC/2005

- (a) Scope: The requirements contained herein apply whenever any CARC topcoats and primers as specified in MIL-DTL-53072 are cited in the contract.
- (b) CARC Primers: Select Army Research Laboratories (ARL) approved powder coat primers can also be used as a replacement for liquid primers such as MIL-P-53022 and MIL-P-53030 primers. Any part that has rust, mill scale, or any other surface contamination must be cleaned prior to the application of any coating IAW TT-C-490.
- (c) End-Item Inspection. After the complete paint finish has been applied and cured\* (see note below), the Contractor shall test and inspect two units per lot for (i) workmanship, (ii) total paint film thickness, and (iii) paint adhesion. Unless otherwise agreed to between the Contractor and the Government quality assurance representative, a lot shall be defined as all units submitted for final Government acceptance at one time. The use of test panels in lieu of actual production units is prohibited.

At final inspection, the cumulative total paint film thickness of pretreatment, primer, and topcoat shall be the sum of the minimum and maximum thicknesses for individual elements of the paint finish as specified in MIL-DTL-53072. The specific number of test locations shall be agreed to by the Government quality assurance representative in advance. In addition, two locations on each sample unit shall be selected to conduct the scribe tape test. The test locations shall be routinely varied among the following:

- (1) Directly adjacent to a weld.
- (2) On or directly adjacent to a machine cut or sheared edge.
- (3) On any mechanically formed surface when lubricants/drawing compounds were used.
- (4) On paint touch-up areas.

The precise location for each scribe tape shall be in an inconspicuous location that has been accepted by the Government quality assurance representative before the test is conducted.

Upon completion of the scribe tape test, the scribe marks shall be feathered into the adjacent area and touched up with the required topcoat so that the tested area conforms to the requirements total DFT specified in MIL-DTL-53072.

\*NOTE: The complete paint finish is defined as the pretreatment, primer, and topcoat applied to the substrate. Curing of the complete paint finish is dependent upon temperature, humidity, and paint film thickness. The time necessary to achieve sufficient adhesion to pass the scribe tape test must be determined by each facility. For purposes of this test, curing at ambient temperature will take 24 days. To accelerate the curing for purposes of product acceptance, the following procedure may be followed: Cure at 190 to 210 degrees Fahrenheit for three hours (this is time at temperature and is therefore material thickness dependent), followed by 7 days at 65 degrees F minimum.

#### (d) Test Methods:

(1) The gage shall be capable of being calibrated. If no other calibration specification or requirement is identified elsewhere in this contract, then the gage shall be calibrated in accordance with ISO 10012.

PIIN/SIIN W56HZV-07-Q-0449 MOD/AMD 0001	CONTINUATION SHEET	Reference No. of Document Bei	Page 5 of 6	
	CONTINUATION SHEET	PIIN/SIIN W56HZV-07-Q-0449	MOD/AMD 0001	

#### Name of Offeror or Contractor:

- (2) Scribe Tape Test. Shall be IAW ASTM D 3359 Method B, six (6) cut pattern.
- (e) Acceptance Criteria:
- (1) Film Thickness. All applicable surfaces shall have complete paint coverage. A minimum of 95% of the surfaces shall meet the minimum and maximum, cumulative dry film thickness requirements. Failure of this test shall result in rejection of the production lot that it represents.
- (2) Scribe Tape Test (Adhesion). The removal of two or more complete squares of top coat, or top coat-primer-pretreatment combination constitutes failure and the production lot is rejected. Removal of overspray does not constitute test failure.
  - (f) CHEMICAL AGENT RESISTANT COATING (CARC) ON WOOD COMPONENTS.
- (1) Wood shall be treated and painted IAW MIL-DTL-53072 section 3.3.4. After treatment, the wood shall provide a paintable surface as described by the paint-ability requirements of Spec TT-W-572, except that the wood species, treatment, and paint shall be the same as furnished for this contract.
- (2) After demonstrating that the paint adhesion requirements are met, and Government inspection/acceptance of this item has occurred, any subsequent flaking and peeling of paint from the wood shall not be considered a defect unless the Government establishes that the flaking and/or peeling of the paint was caused by defective workmanship in the application of the paint or the preparation of the painted surface.

[End of Clause]

# CONTINUATION SHEET Reference No. of Document Being Continued

PIIN/SIIN W56HZV-07-Q-0449

MOD/AMD 0001

Page 6 of 6

#### Name of Offeror or Contractor:

INSTRUCTIONS, CONDITIONS, AND NOTICES TO OFFERORS

4 ADDED 52.211-4049 (TACOM)

PART NUMBERS NOT CURRENTLY APPROVED

NOV/1982

As specified elsewhere in this solicitation, part or all of the contract item to be procured hereunder is restricted to certain approved manufacturer's part numbers as set forth in the Schedule and/or the Technical Data Package. Any firm that produces an item which it believes to be equivalent to one of these approved part numbers is hereby encouraged to have such item tested and approved, so that the item will be eligible to be bought on future acquisitions. Please write to the attention of the buyer at the address indicated on the cover page of this solicitation and request a statement of the procedures by which items can be tested and approved for procurement. Such an enquiry should cite the applicable National Stock Number (NSN), the already approved part number, the part number of the item which the enquirer believes to be identical to our approved item, and a brief statement of the basis on which the new item is believed to be equivalent to our already approved item.

[End of Provision]

5 ADDED 52.211-4051 (TACOM)

NOTICE REGARDING SOURCE-CONTROLLED COMPONENTS

FEB/1998

- (a) Please see the provision entitled ACQUISITION OF MANUFACTURER'S PART NUMBER: COMPONENTS in this solicitation. At least one component of the item to be purchased under this acquisition is restricted to specified manufacturer's part numbers as set forth in the Technical Data Package. It is the responsibility of each offeror to ensure the availability of sufficient quantities of such source—controlled components before making an offer in response to this solicitation. Except as described in paragraph (b) below, offers that propose to substitute alternatives to the source—controlled components, even if the substitute items are represented as equivalent in all respects to the source—controlled components, will not be considered for contract award.
  - (b) Required Approval for Alternatives to the Source-Controlled Component:
- (1) By meeting the following conditions, a firm may submit an offer conditioned on acceptance by the Government of alternatives to the source-controlled component(s) listed in the Technical Data Package:
  - -- <u>Prior</u> to receipt of this solicitation, the firm must have received written TACOM approval of a test procedure on its proposed equivalent component.
  - -- The firm must indicate in its offer the date of the written TACOM approval, and the name and title of the approving official.
  - -- The firm must certify in its offer that it is in the process of having its item independently tested per the approved test procedure to demonstrate full physical, functional, and mechanical interchangeability of its part with an already-approved part cited in this solicitation, or that it is awaiting final TACOM engineering approval of the summary report furnished at the conclusion of testing; and
  - -- The firm must have secured final written approval of its part from TACOM engineering by the time of bid opening, (in the case of formally advertised acquisitions), or by the time of contract award, (in the case of negotiated acquisitions).
- (2) Notwithstanding the foregoing, the Procuring Contracting Officer has the right to waive the above conditions in making an award when it is clearly established, in his sole discretion, that written approval of a nonlisted part from TACOM engineering can be obtained without delay in the anticipated date of award.

When either of the foregoing conditions are met, the Government reserves the right to make an award where use of the equivalent item is authorized in lieu of the source-controlled item. Where the foregoing conditions are not met, offeror will not be eligible for award unless he agrees to furnish the source-controlled item(s) from the indicated source(s).

(c) Any firm that manufactures or regularly sells an item which it views as equivalent in all respects to one of our required components, but that has not initiated approved qualification testing in order to demonstrate that its part is totally equivalent to the required component, should see the notice entitled PART NUMBERS NOT CURRENTLY APPROVED, located elsewhere in this Section L.

[End of Provision]